

MW ↓ lower to higher	Polyol Name	Base	Visc. (cps)	OH no.	Eq. MW	F.	Acid mgKOH/g	Water %
380	Castpol gt400	castor	900	400	141	2.7	<2	<0.08
420	Castpol tt400	castor	1200	400	140	3.0		
425	Castpol 264	castor	400	264	213	2.0		
450	Castpol 500	castor	300	265	214	2.1		
550	Castpol D-220	castor	150	200	275	2.0		
625	Castpol 912	castor	500	200	284	2.2		
900	Castpol 250	castor	3000	165	346	2.6		

870	Castpol 115	castor	3000	160	348	2.5	<2	<0.08
700	Castpol PT-305	castor	1600	285	194	3.6		
600	Castpol PM-365	castor	1900	365	154	3.9		
800	Castpol 2807	castor	1250	280	200	4.0		
800	Castpol D-143	castor	600	140	400	2.0		

1300	Castpol P-175	castor	1300	175	317	4.1	<2	<0.08
1000	Castpol D-1000L	castor	600	125	455	2.2		
2000	Castpol A-116	castor	1700	110	513	3.9		

2000	Castpol D-1052	castor	500	50	1111	1.8	<2	<0.08
2000	Castpol D-2000L	castor	1400	55	1000	2.0		
2000	Castpol D-2012L	castor	1600	55	1000	2.0		

Elmira Industrial Supplies u.g. | 2, Charlottenstraße, 10969, Berlin.

+49 01633047733 | [sales@elmirasupplies.com](mailto:sales@elmirasupplies.com)