

MW ↓lower to higher	Oil Name	Base	Visc. at 25°C (cps)	colour (gardner)	OH no.	Eq. MW	F.	Acid mgKOH/ g	Water %
304	XFN 10.85	cardanol	40-60	10 to 12	180-200	304	1	5 max	0.5 max
304	XFN 10.91	cardanol	40-60	8 to 10	180-200	304	1	5 max	0.3 max
304	XFN 10.91	cardanol	40-60	4 to 6	180-200	304	1	5 max	0.3 max
930	LM-FSG 300	castor	950-1100	2	160-168	344	2.7	0.8 max	0.02 max

[Elmira Industrial Supplies u.g. | 2, Charlottenstraße, 10969, Berlin.](mailto:sales@elmirasupplies.com)

[+49 01633047733 | sales@elmirasupplies.com](mailto:sales@elmirasupplies.com)